



Planos

Lámina Negra

Calibre	Espesor		Peso Teórico		Peso aproximado por hoja			
	pulg.	mm	kg/m ²	kg/pie ²	3' x 8'	3' x 10'	4' x 8'	4' x 10'
1/4"	0.25	6.35	49.83	4.63	111.12	138.89	148.15	185.19
3	0.239	6.07	48.82	4.54	108.85	136.07	145.14	181.42
4	0.2242	5.69	45.77	4.25	102.05	127.57	136.07	170.09
5	0.209	5.31	42.72	3.97	95.25	119.06	127	158.75
6	0.194	4.93	39.67	3.69	88.45	110.56	117.93	147.42
3/16"	0.187	4.75	37.28	3.46	83.11	103.89	110.82	138.52
7	0.179	4.55	36.62	3.4	81.65	102.06	108.87	136.08
8	0.164	4.17	33.57	3.12	74.85	93.56	99.8	124.75
9	0.1495	3.8	30.52	2.84	68.05	85.06	90.73	113.42
10	0.1345	3.42	27.46	2.55	61.23	76.53	81.64	102.04
1/8"	0.125	3.18	24.92	2.31	55.56	69.45	74.08	92.6
11	0.1196	3.04	24.41	2.27	54.43	68.03	72.57	90.71
12	0.1046	2.66	21.36	1.98	47.63	59.53	63.5	79.38
13	0.0897	2.28	18.3	1.7	40.8	51	54.4	68
14	0.0747	1.9	15.26	1.42	34.02	42.53	45.37	56.71
15	0.0673	1.71	13.42	1.25	29.91	37.39	39.88	49.85
16	0.0598	1.52	12.2	1.13	27.2	34	36.27	45.34
17	0.0538	1.37	10.72	1	23.91	29.89	31.88	39.85
18	0.0478	1.21	9.76	0.91	21.76	27.2	29.02	36.27
19	0.0418	1.06	8.33	0.77	18.58	23.22	24.77	30.96
20	0.0359	0.91	7.32	0.68	16.32	20.4	21.76	27.2
21	0.0329	0.84	6.56	0.61	14.62	18.28	19.5	24.37
22	0.0299	0.76	6.1	0.57	13.6	17	18.13	22.67
23	0.0269	0.68	5.36	0.5	11.96	14.95	15.94	19.93
24	0.0239	0.61	4.88	0.45	10.88	13.6	14.51	18.13
25	0.0209	0.53	4.17	0.39	9.29	11.61	12.39	15.48
26	0.0179	0.45	3.66	0.34	8.16	10.2	10.88	13.6
27	0.0164	0.42	3.27	0.3	7.29	9.11	9.72	12.15
28	0.0149	0.38	3.05	0.28	6.8	8.5	9.07	11.33
29	0.0135	0.34	2.69	0.25	6	7.5	8	10
30	0.012	0.3	2.44	0.23	5.44	6.8	7.25	9.07

Lámina lisa rolada en caliente y frío procedente de rollo.

Placas.

Espesor			Peso		Peso teórico por placa (kg) en medidas			
Pulgadas	Milésimas	Milímetros	kg/m ²	kg/pie ²	3' x 8'	3' x 10'	4' x 8'	4' x 10'
3/16	188	4.76	37.39	3.47	83.36	104.2	111.14	138.93
1/4	250	6.35	49.85	4.63	111.14	138.93	148.19	185.24
5/16	313	7.94	62.31	5.79	138.93	173.66	185.24	231.55
3/8	375	9.53	74.77	6.95	166.72	208.39	222.29	277.86
7/16	438	11.11	87.23	8.1	194.5	243.13	259.34	324.17
1/2	500	12.7	99.7	9.26	222.29	277.86	296.38	370.48
5/8	625	15.88	124.62	11.58	277.86	347.32	370.48	463.1
3/4	750	19.05	149.54	13.89	333.43	416.79	444.58	555.72
7/8	875	22.23	174.47	16.21	389	486.25	518.67	648.34
1	1000	25.4	199.39	18.52	444.58	555.72	592.77	740.96
1 1/4	1250	31.75	249.24	23.15	555.72	694.65	740.96	926.2
1 1/2	1500	38.1	299.09	27.79	666.86	833.58	889.15	1,111.44
1 3/4	1750	44.45	348.93	32.42	778.01	972.51	1,037.34	1,296.68
2	2000	50.8	398.78	37.05	889.15	1,111.44	1,185.53	1,481.92
2 1/2	2500	63.5	498.48	46.31	1,111.44	1,389.30	1,481.92	1,852.40
3	3000	76.2	598.17	55.57	1,333.73	1,667.16	1,778.30	2,222.88
3 1/2	3500	88.9	697.87	64.83	1,556.01	1,945.02	2,074.68	2,593.35
4	4000	101.6	797.56	74.1	1,778.30	2,222.88	2,371.07	2,963.83
4 1/2	4500	114.3	897.26	83.36	2,000.59	2,500.73	2,667.45	3,334.31
5	5000	127	996.95	92.62	2,222.88	2,778.59	2,963.83	3,704.79
6	6000	152.4	1,196.34	111.14	2,667.45	3,334.31	3,556.60	4,445.75

Lámina Antiderrapante.

Calibre	Espesor		Peso		Peso teórico por hoja de lámina y placa (kg)			
	Pulgadas	Milímetros	kg/pie ²	kg/m ²	3' x 8'	3' x 10'	4' x 8'	4' x 10'
3/8"	0.375	9.53	7.42	79.74	177.99	222.49	237.32	296.65
5/16"	0.313	7.94	6.26	67.31	150.23	187.79	200.31	250.38
1/4"	0.25	6.35	5.1	54.87	122.47	153.09	163.29	204.12
3/16"	0.188	4.76	3.95	42.43	94.71	118.39	126.28	157.85
1/8"	0.125	3.18	2.79	30	66.95	83.69	89.27	111.58
12	0.105	2.66	2.38	25.61	57.15	71.44	76.2	95.25
14	0.075	1.9	1.7	18.29	40.82	51.03	54.43	68.04